



Product Specifications

<i>Description</i>		Textured Loop Pile Carpet	
<i>Pile Fibre</i>		100% Antron Lumena Nylon	
<i>Dye Method</i>		Solution Dyed	
<i>Method of Manufacture</i>		Tufted	
<i>Machine Gauge</i>		1/12 th 47 stitches per 10 cm	
<i>Pile Weight</i>		650 g m ²	
<i>Tuft Density</i>		211,500 tufts per m ²	
<i>Pile Height</i>		2.9 mm	
<i>Total Thickness</i>		5.8 mm	
<i>Total Weight</i>		4,075 g m ²	
<i>Backing</i>		Modified Bitumen	
<i>Lead Time</i>		Ex-Stock 48 Hours Ex-Production 6-8 Weeks	
<i>Format</i>		Tiles (bitBAC)	Planks (bitBAC)
<i>Product Size</i>		500 mm x 500 mm	1000 mm x 250 mm
<i>Pack Size</i>		20 Tiles 5 m ²	20 Planks 5 m ²
<i>Availability</i>		Stocked	Made-to-Order
<i>Minimum Order Quantity</i>		1 Box 5 m ²	500 m ²
<i>Installation Method</i>		Loose-Lay on Tackifier	Loose-Lay on Tackifier
<i>Recommended Laying Pattern</i>		Brick Non-Directional	Half Drop
<i>Recommended Adhesives</i>	<i>F Ball & Co</i>	F41	F41
	<i>Uzin</i>	U2100 Universal Tackifier	U2100 Universal Tackifier

Performance Specifications

<i>Format</i>		Tiles & Planks (bitBAC)	
<i>Wear Rating</i>	<i>EN 1307</i>	33 Heavy Commercial Use	
<i>Castor Chair Rating</i>	<i>EN 985</i>	≥ 2.4r Continuous Use	
<i>Flammability Rating</i>	<i>EN 13501-1:2020</i>	B _{fl} S1	
<i>Impact Sound Insulation</i>	<i>EN ISO 10140</i>	ΔLw 22 dB	
<i>Sound Absorption</i>	<i>EN ISO 11654</i>	αw 0.15	
<i>Thermal Resistance</i>	<i>BS 4745:2005</i>	0.49 Togs Suitable for UFH	
<i>Electrostatic Properties</i>	<i>EN ISO 6356</i>	≤ 2 kV Antistatic	
<i>Colourfastness to Light</i>	<i>ISO EN 105-B02</i>	> 6 (on a scale of 1-8)	
<i>Formaldehyde Emissions</i>	<i>EN 717-1:2005</i>	Class E1	